

Technical Data Sheet: Adhesive Backer 330 TS

Adhesive Backer 330 TS

Technical Data Sheet		
Thickness	.008"	
Estimated cost (large volume)	Call or email for pricing.	
Minimum Glue Line temp under full Temperature & Pressure	275°F	
Bonding Temperature Under Full Temperature & Pressure	275°f	135° C
Minimum Pressure	60 - 150 PSI	
Base Resin	Acrylic/Melamine	
Flame Resistant	No	
Water Resistant	Yes	
Carrier	Thick Cellulose Blend	

Recommended bonding surfaces

Cork, Cotton, Leather, Melamine, Paper, Phenolic, Wood Veneer, Chip Board, Wool; Also good bonding with- Carbon, Polyester & 2 Ply Faces

About our 330 TS

This veneer backer is a high performance, one or two sided flexible adhesive backer allowing activation at low temperature settings. Our 330 TS provides a consistent bond with excellent heat and moisture resistance. The bond of our 330 TS to recommended surfaces allows for a consistent application of bonding properties throughout the surface preventing blistering, grain swells and cracking.

1267 House St, NE \cdot Belmont, MI \cdot 49306 \cdot USA Phone: 616-887-8257 \cdot Fax: 616-887-7910 \cdot Email: sales@lenderink.com

www.lenderink.com • www.dryfilmadhesive.com